



Textile Testing

553 76th Street · Byron Center, MI 49315 Phone: 616.559.6123 Fax: 616.559.6119



TESTING CERT. #3193.01

Report Number: 48915

Date: 11-10-2011

For the Account Of: Bru Textiles
Satenrozen 2a
B-2550 Kontich
Belgium
Contact: Tineke Verbruggen

Client's Identification: Delis

Test Performed Federal Motor Vehicle Safety Standard (FMVSS) 302 - January 1971

TEST DATA

	<u>Specimen #</u>	<u>Burning Time Beyond 38 mm (seconds)</u>	<u>Burn Distance Beyond 38 mm (mm)</u>	<u>Burn Rate (mm/minute)</u>	<u>Code</u>
Length	1	0.0	0.0	N/A	DNI
	2	0.0	0.0	N/A	DNI
	3	0.0	0.0	N/A	DNI
	4	0.0	0.0	N/A	DNI
	5	0.0	0.0	N/A	DNI
Width	6	0.0	0.0	N/A	DNI
	7	0.0	0.0	N/A	DNI
	8	0.0	0.0	N/A	DNI
	9	0.0	0.0	N/A	DNI
	10	0.0	0.0	N/A	DNI

Specimen Tested:

- Standard
- Modified, 10 mil wire spaced at 25mm intervals across 51 mm width opening:
 - Test item was less than 56 mm wide
 - Specimen softens and bends at flaming end, which results in erratic burning

ABBREVIATIONS USED

- SE(B)** Self-extinguishing with burn rate. Specimen ignites; Time of burning after passing 38 mm is greater than 60 seconds and 51 mm before extinguishing.
- DNI** Does not ignite. Specimen does not support combustion during or after ignition.
- SE** Self-Extinguishing. Specimen ignites but does not burn to the timing zone, which starts at 38 mm.
- SE/NBR** Self-Extinguishing/No burn rate. Specimen ignites; burning progresses to the 38 mm timing start line and extinguishes within 51 mm beyond the start line and 60 seconds.
- B** Specimen ignites. Burning progresses more than 51 mm beyond the 38 mm timing start line. Burn rate is calculated.

NOTES

Test Conditions: 70 ±2°F, 65 ±2% Relative Humidity

ACCEPTANCE CRITERIA

1. Burn rate must not exceed 102 mm/min for any specimen

CONCLUSION Based on the above Results and Acceptance Criteria, the item tested:

- Passes
- Fails

CERTIFICATION: I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

Authorized Signature