



Textile Testing

553 76th Street · Byron Center, MI 49315 Phone: 616.559.6123 Fax: 616.559.6119

Report Number: 48915
Date: 11-10-2011

For the Account Of: Bru Textiles
Satenrozen 2a
B-2550 Kontich
Belgium
Contact: Tineke Verbruggen

Client's Identification: Delis

Test Performed NY / NJ Port Authority Specifications Governing the Flammability of Drapery and Curtain Materials - 1992

TEST DATA

<u>Specimen #</u>	<u>AFTERFLAME</u> <u>SECONDS</u>	<u>DRIP BURN</u> <u>SECONDS</u>	<u>CHAR LENGTH</u> <u>INCHES</u>	<u>MELT LENGTH</u> <u>INCHES</u>
1	0	0	4.0	4.0
2	0	0	3.8	3.8
3	0	0	4.0	4.0
AVERAGE WARP	0	0	3.9	3.9
4	0	0	3.8	3.8
5	0	0	3.5	3.5
6	0	0	3.8	3.8
AVERAGE FILL	0	0	3.7	3.7

Tested:

- Initially
- After Laundering
- After Dry Cleaning

NOTES

Test Conditions: 70 ±2°F, 65 ±2% Relative Humidity

ACCEPTANCE CRITERIA


1. Average Burn Length cannot exceed **8 inches** maximum average.
2. Average Flame Time after removal of the flame source may not exceed **15 seconds**.
3. Drippings from the test specimen may not continue to flame for more than an average of **5 seconds** after falling.
4. Melt Length, when observed, is reported. However, it is not factored into the Acceptance Criteria.

CONCLUSION

Based on the above Results and Acceptance Criteria, the item tested:

- Complies
- Does Not Comply

CERTIFICATION: I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.



Authorized Signature