

TEST REPORT

Date: 09 January 12
TN 412593

REPORT ON

ORDER NUMBER Not Stated

One sample of woven fabric, submitted by Brigitte Gyselinck, on behalf of Bru Textiles NV, Satenrozen 2a B - 2550 Kontich Belgium

IDENTIFICATION AND INFORMATION RECEIVED

Design Name: Helio
Quality: Not Stated
End Use: Curtains & Drapes / Accessories
Stated Composition: 100% Inherent Permanent Polyester FR

Work received 15/12/2011
Work completed 09/01/2012

TESTS REQUESTED

British Standard: Methods of Test

Flammability of Fabrics for Curtains and Drapes: Type C



Polly Taylor
Assistant Manager

RPPT/

This certificate comprises 3 pages and is subject to the UL-STR conditions of business. ** denotes this test is not on our UKAS schedule

All results relate only to the sample(s) received for testing.

This test report shall not be reproduced except in full without the prior written permission of the testing laboratory.

RESULTS

British Standard: Methods of Test

Flammability of Fabrics for Curtains and Drapes: BS 5867: Part 2: Type C: 2008

“The results may not apply to situations where there is restricted air supply or prolonged exposure to large sources of intense heat as in a conflagration.”

Tested to BS EN ISO 15025: 2002 – Procedure A: Surface Ignition

Gas Used: Propane

Testing Temperature: 16°C

R.H.: 42%

As Received

<u>5 Seconds</u>	<u>Length of Fabric</u>		<u>Width of Fabric</u>	
	<u>1</u>	<u>2</u>	<u>3</u>	<u>4</u>
	Face	Reverse	Face	Reverse
Flame Reached on Edge	No	No	No	No
Flaming Debris	No	No	No	No
Afterflame Time (Secs)	0.0	0.0	0.0	0.0
Afterglow Time (Secs)	0.0	0.0	0.0	0.0

<u>15 Seconds</u>	<u>Length of Fabric</u>		<u>Width of Fabric</u>	
	<u>1</u>	<u>2</u>	<u>3</u>	<u>4</u>
	Face	Reverse	Face	Reverse
Flame Reached on Edge	No	No	No	No
Flaming Debris	No	No	No	No
Afterflame Time (Secs)	0.0	0.0	0.0	0.0
Afterglow Time (Secs)	0.0	0.0	0.0	0.0

<u>20 Seconds</u>	<u>Length of Fabric</u>		<u>Width of Fabric</u>	
	<u>1</u>	<u>2</u>	<u>3</u>	<u>4</u>
	Face	Reverse	Face	Reverse
Flame Reached on Edge	No	No	No	No
Flaming Debris	No	No	No	No
Afterflame Time (Secs)	0.0	0.0	0.0	0.0
Afterglow Time (Secs)	0.0	0.0	0.0	0.0

<u>30 Seconds</u>	<u>Length of Fabric</u>		<u>Width of Fabric</u>	
	<u>1</u>	<u>2</u>	<u>3</u>	<u>4</u>
	Face	Reverse	Face	Reverse
Flame Reached on Edge	No	No	No	No
Flaming Debris	No	No	No	No
Afterflame Time (Secs)	0.0	0.0	0.0	0.0
Afterglow Time (Secs)	0.0	0.0	0.0	0.0

Assessment – As Received

The fabric complied with the requirements of BS 5867: Part 2 Type C.

After launder

<u>5 Seconds</u>	<u>Length of Fabric</u>		<u>Width of Fabric</u>	
	<u>1</u>	<u>2</u>	<u>3</u>	<u>4</u>
	Face	Reverse	Face	Reverse
Flame Reached on Edge	No	No	No	No
Flaming Debris	No	No	No	No
Afterflame Time (Secs)	0.0	0.0	0.0	0.0
Afterglow Time (Secs)	0.0	0.0	0.0	0.0

<u>15 Seconds</u>	<u>Length of Fabric</u>		<u>Width of Fabric</u>	
	<u>1</u>	<u>2</u>	<u>3</u>	<u>4</u>
	Face	Reverse	Face	Reverse
Flame Reached on Edge	No	No	No	No
Flaming Debris	No	No	No	No
Afterflame Time (Secs)	0.0	0.0	0.0	0.0
Afterglow Time (Secs)	0.0	0.0	0.0	0.0

<u>20 Seconds</u>	<u>Length of Fabric</u>		<u>Width of Fabric</u>	
	<u>1</u>	<u>2</u>	<u>3</u>	<u>4</u>
	Face	Reverse	Face	Reverse
Flame Reached on Edge	No	No	No	No
Flaming Debris	No	No	No	No
Afterflame Time (Secs)	0.0	0.0	0.0	0.0
Afterglow Time (Secs)	0.0	0.0	0.0	0.0

<u>30 Seconds</u>	<u>Length of Fabric</u>		<u>Width of Fabric</u>	
	<u>1</u>	<u>2</u>	<u>3</u>	<u>4</u>
	Face	Reverse	Face	Reverse
Flame Reached on Edge	No	No	No	No
Flaming Debris	No	No	No	No
Afterflame Time (Secs)	0.0	0.0	0.0	0.0
Afterglow Time (Secs)	0.0	0.0	0.0	0.0

Assessment – After Launder

The fabric complied with the requirements of BS 5867: Part 2 Type C.



Polly Taylor
Assistant Manager