



For the Account Of: Bru Textiles
Satenrozen 2a
B-2550 Kontich
Belgium
Contact: Tineke Verbruggen

Client's Identification: Helio

Test Performed California Fire Marshal Title 19: Section 1237 Small Scale Test – Interior Materials Qualifications (Proposed Revision – 8/9/93)

TEST DATA

<u>Specimen #</u>	<u>AFTERFLAME</u> <u>(SECONDS)</u>	<u>CHAR LENGTH</u> <u>(INCHES)</u>
Length		
1	0.0	5.1
2	0.0	4.0
3	0.0	4.7
4	0.0	4.9
5	0.0	5.1
AVERAGE	0.0	
6	0.0	4.9
7	0.0	3.3
8	0.0	4.3
9	0.0	4.5
10	0.0	4.1
AVERAGE	0.0	

Tested:

- Initially
- After Laundering
- After Dry Cleaning

ACCEPTANCE CRITERIA


1. Average Flame Time (after flame) after removal of the flame source may not exceed **4.0 seconds** for length or width
2. Char length may not exceed **6.0 inches** for any individual specimen.

CONCLUSION

Based on the above Results and Acceptance Criteria, the item tested:

- Complies
- Does Not Comply

CERTIFICATION: I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above. These results were obtained from an outside source.



Authorized Signature