



Textile Testing

553 76th Street · Byron Center, MI 49315 Phone: 616.559.6123 Fax: 616.559.6119



Report Number: 49571
Date: 12-15-2011

For the Account Of: Bru Textiles
Satenrozen 2a
B-2550 Kontich
Belgium
Contact: Tineke Verbruggen

Client's Identification: Helio

Test Performed NFPA 260 Standard Methods of Tests and Classification System for Cigarette Ignition Resistance of Components of Upholstered Furniture – 2009: Fabric Cover Test and UFAC Fabric Classification Test Method – 1990

TEST DATA

Specimen #	Char Length (inches)
1	0.7
2	0.7
3	0.7

NOTES

Test Conditions: 70 ±2°F, 65 ±2% Relative Humidity

ACCEPTANCE CRITERIA


1. If the test specimen has no ignition, or if no individual specimen yields a vertical char of 44 mm (1.75 in.) or less, the fabric is classified a UFAC and NFPA Class I cover fabric.
2. If the vertical char of the test specimen greater than 45 mm (1.75 in.), the fabric is classified a UFAC Class II cover fabric.
3. If an obvious ignition of the polyurethane substrate occurs on the test assembly, the fabric is classified a UFAC Class II cover fabric.

CONCLUSION

Based on the above Results and Acceptance Criteria, the item tested is:

- Class I
- Class II

CERTIFICATION: I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.


Authorized Signature