

CERTIFICATE OF TESTING

For the Account Of: Bru Textiles
Satenrozen 2a
B2550 Kontich
Belgium
Contact: Tineke Verbruggen

Client's Identification: FR-One Genial

TEST PERFORMED California Fire Marshal Title 19: Section 1237 Small Scale Test – Interior Materials Qualifications
(Proposed Revision – 8/9/93)

TEST RESULTS

Specimen	Afterflame (s)	Char Length (in)
<i>Warp</i>		
1	0	4.9
2	0	4.6
3	0	3.1
4	0	4.0
5	0	3.8
Average	0.0	4.1
<i>Fill</i>		
6	0	4.3
7	0	4.0
8	0	4.9
9	0	3.4
10	0	4.4
Average	0.0	4.2

Tested:

- Initially
- After Laundering
- After Dry Cleaning

ACCEPTANCE CRITERIA

1. Average Flame Time (after flame) after removal of the flame source may not exceed **4.0 seconds** for length or width
2. Char length may not exceed **6.0 inches** for any individual specimen.
3. When a part of the char length is melt away due to heat from the flame source and not from propagating flame, the sample submitted meets the requirements of Title 19 – California Code of Regulations, Section 1237 and 1237.1 for fabrics weighing less than 4 oz./sq.yd. These specimens shall be marked with an asterisk (*) next to the char length.

CONCLUSION

Based on the above Results and Acceptance Criteria, the item tested:
 Complies
 Does Not Comply

CERTIFICATION I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

Authorized Signature-MB

