



530-535, Eskdale Road, Winnersh Triangle, Reading, RG41 5TS

T: 01189 73340

W: ul.com/consumer-products

TEST REPORT

Date: 26 February 16

TN 439292

Amended(1)

REPORT ON

ORDER NUMBER Not Stated

One sample of Upholstery , submitted by Tineke Verbruggen, on behalf of Bru Textiles NV, Satenrozen 2a B - 2550 Kontich Belgium

IDENTIFICATION AND INFORMATION RECEIVED

FR-One Genii: Gaheris, Griflet, Gerain, Gorlois

End Use: Upholstery

Stated Composition: Not Stated

Work received 15/01/2016

Work completed 18/02/2016

TESTS REQUESTED

British Standard: Methods of Test

Flammability of Fabrics for Curtains and Drapes: Type B

Kathryn Cutts
Assistant Laboratory Operations Manager

RPPT/

This certificate comprises 2 pages and is subject to the UL-STR conditions of business

** denotes this test is not on our UKAS schedule

All results relate only to the sample(s) received for testing.

This test report shall not be reproduced except in full without the prior written permission of the testing laboratory.

The test results provided do not take into account Uncertainty of Measurement. The uncertainty budgets may be supplied on request



0517

Flammability of Fabrics for Curtains and Drapes: BS 5867: Part 2: Type B: 2008

“The results may not apply to situations where there is restricted air supply or prolonged exposure to large sources of intense heat as in a conflagration.”

Tested to BS EN ISO 15025: 2002 – Procedure A: Surface Ignition

15 Second Flame Application Time

Gas Used: Propane

Testing Temperature: Between 15°C & 30°C R.H.: Between 20% & 65% %
°C

Tested as Received

As Received	<u>Length of Fabric</u>			<u>Width of Fabric</u>		
	<u>1</u>	<u>2</u>	<u>3</u>	<u>4</u>	<u>5</u>	<u>6</u>
Flame Reached on Edge	No	No	No	No	No	No
Flaming Debris	No	No	No	No	No	No
Afterflame Time (Secs)	0.0	0.0	0.0	0.0	00	0.0
Afterglow Time (Secs)	18.6	33.3	19.7	3.0	0.0	0.0

Assessment – As Received


The fabric **complies** with the requirements of BS 5867: Part 2 Type B.

After Launder	<u>Length of Fabric</u>			<u>Width of Fabric</u>		
	<u>1</u>	<u>2</u>	<u>3</u>	<u>4</u>	<u>5</u>	<u>6</u>
Flame Reached on Edge	No	No	No	No	No	No
Flaming Debris	No	No	No	No	No	No
Afterflame Time (Secs)	0.0	0.0	0.0	0.0	0.0	0.0
Afterglow Time (Secs)	0.0	0.0	0.0	0.0	0.0	0.0

Assessment – After Launder

The fabric **complies** with the requirements of BS 5867: Part 2 Type B.

The above analysis was carried out on our behalf by a third party laboratory



Kathryn Cutts
Assistant Laboratory Operations Manager