

ANALYSIS REPORT
SCC Accreditation No.: 40‡

Mr Tineke Verbruggen
Bru Textiles nv

Date: May 6, 2016
Report: 3489-010-89071A

IDENTIFICATION: One fabric: FR-One Genii-chenille
Received: April 29, 2016

STANDARD:

TEST: Flame Tests of Flame-Resistant Fabrics and Films-Small-Flame Test CAN/ULC-S109-14
- As received

TEST CONDITIONS: Gas used : methane; Gas pressure used: $2\frac{1}{2} \pm \frac{1}{4}$ psi;
Specimens tested as received only.
Specimens conditioned for 30 min at $105 \pm 2^{\circ}\text{C}$;
Cooling time in a desiccator: 30 minutes
Date tested: May 5, 2016

RESULTS:

Individual Data

Afterflame (s) - Residues - Length: 0 0 0 0 0

Afterflame (s) - Residues - Width: 0 0 0 0 0

Damaged length (mm) - Length: 125 133 122 117 93

Damaged length (mm) - Width: 100 104 98 89 96


Damaged length (mm) - Average: 108

REQUIREMENTS: Portions or residues of the material which break or drip from the test specimens shall not continue to flame for more than 2 seconds on the floor of the test cabinet.
Maximum Average Damaged Length for 10 specimens : 165 mm;
Maximum Damaged Length for any specimen : 190 mm.

Prepared by:


François Milhomme, Tech.
Technician

Approved by: Édith Dion Marcil


For: Valério Izquierdo
Vice-President

Date: May 6, 2016

****For any information concerning this report, please contact Valério Izquierdo.****

The reports are identified by an alphanumeric code, the last character refers to the number of revision(s), this is emitted in ascending order. The samples in relation to this test are retained for a period of 30 days following the expedition day of the written report, unless other instructions are received. The fees for all services after the tests are 125.00 \$ per hour and for appraisal in Court, 195.00\$ per hour. The above reported results refer exclusively to the samples submitted for evaluation. This analysis report cannot be partly used or reproduced, unless in whole, without CTT Group prior written consent. ‡ CTT Group is accredited by the SCC for specific tests as listed on www.scc.ca. For customer's complete address, please refer to the front page.

ANALYSIS REPORT
SCC Accreditation No.: 40‡

Mr Tineke Verbruggen
Bru Textiles nv

Date: May 6, 2016
Report: 3489-010-89071A

IDENTIFICATION: One fabric: FR-One Genii-chenille
Received: April 29, 2016

STANDARD:

TEST: Flame Tests of Flame-Resistant Fabrics and Films-Large-Flame Test CAN/ULC-S109-14
- As received

TEST CONDITIONS: Gas used : methane; Gas pressure used: 1.06 kPa;
Specimens tested as received only.
Configuration of specimens: Folded ;
Specimens conditioned for 30 min at 105 ± 2°C ;
Cooling time in a desiccator: 1 hour
Date tested: May 5, 2016

RESULTS: Individual Data

Afterflame (s) - Residues - Length: 0 0


Afterflame (s) - Residues - Width: 0 0

Folded/Length of surface spread (mm) - Length: 142 119


Folded/Length of surface spread (mm) - Width: 83 103

REQUIREMENTS: Portions or residues of the material which break or drip from the test specimens shall not continue to flame for more than 2 seconds on the floor of the test cabinet.
Surface spread: shall not exceed 635 mm above the tip of the test flame (folded).

Prepared by:


Julien Gagné, Tech.
Technician

Approved by: Édith Dion Marcil


For: Valério Izquierdo
Vice-President

Date: May 6, 2016

****For any information concerning this report, please contact Valério Izquierdo.****

The reports are identified by an alphanumeric code, the last character refers to the number of revision(s), this is emitted in ascending order. The samples in relation to this test are retained for a period of 30 days following the expedition day of the written report, unless other instructions are received. The fees for all services after the tests are 125.00 \$ per hour and for appraisal in Court, 195.00\$ per hour. The above reported results refer exclusively to the samples submitted for evaluation. This analysis report cannot be partly used or reproduced, unless in whole, without CTT Group prior written consent. ‡ CTT Group is accredited by the SCC for specific tests as listed on www.scc.ca. For customer's complete address, please refer to the front page.