

**CERTIFICATE OF TESTING**

For the Account Of: Bru Textiles  
Satenrozen 2a  
B2550 Kontich  
Belgium  
Contact: Brigitte Gyselincx

Client's Identification: FR- One Jaba

**TEST PERFORMED** Boston Fire Test BFD IX – 1: May 2003

**TEST RESULTS**

Specimen	After Flame (s)	Char Length (in)	Propagation Afterglow (s)	Non-Propagating Afterglow (s)
1	0	3.8	0	0
2	0	4.0	0	0
3	0	3.6	0	0
4	0	3.8	0	0
5	0	3.4	0	0
6	0	3.4	0	0

**NOTES**

**Test Conditions:** 70 ±4°F, 65 ±5% Relative Humidity  
**Sampling Method:** As Received


**ACCEPTANCE CRITERIA**

After Flame 2.0 seconds, maximum  
Flame Propagation Distance 6.0 inches, maximum  
Propagation Afterglow 40.0 seconds, maximum  
Non Propagating Afterglow 80.0 seconds, maximum (in charred area)

**CONCLUSION**

Based on the above Results and Acceptance Criteria, the item tested:  
 Complies  
 Does Not Comply

**CERTIFICATION** I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

  
Authorized Signature CR