

CERTIFICATE OF TESTING

For the Account Of: Bru Textiles
Satenrozen 2a
B2550 Kontich
Belgium
Contact: Brigitte Gyselinck

Client's Identification: FR- One Jest

TEST PERFORMED Boston Fire Test BFD IX – 1: May 2003

TEST RESULTS

Specimen	After Flame (s)	Char Length (in)	Propagation Afterglow (s)	Non-Propagating Afterglow (s)
1	0	3.0	0	0
2	0	2.8	0	0
3	0	2.3	0	0
4	0	1.8	0	0
5	0	2.1	0	0
6	0	2.0	0	0

NOTES

Test Conditions: 70 ±4°F, 65 ±5% Relative Humidity
Sampling Method: As Received


ACCEPTANCE CRITERIA

After Flame 2.0 seconds, maximum
Flame Propagation Distance 6.0 inches, maximum
Propagation Afterglow 40.0 seconds, maximum
Non Propagating Afterglow 80.0 seconds, maximum (in charred area)

CONCLUSION

Based on the above Results and Acceptance Criteria, the item tested:
 Complies
 Does Not Comply

CERTIFICATION I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.


Authorized Signature CR