

Document number: 201700039  
 Fabric reference: Jest  
 (ecru)  
 Customer: BRU Textiles  
 Satenrozen 2a  
 B-2550 Kontich

Report date: 13/01/2017  
 Date analyses: 12/01/2017 - 13/01/2017  
 Place analyses: Labotex  
 Date of request: 6/01/2017  
 Samples received: 5/01/2017

Testing and conditioning in standard atmosphere, T (20±2)°C and RH (65±4)%

## Specification

## Results

## Remarks

!


### Burning behaviour of fabrics for curtains drapes

EN13773

conditioning min 24h in standard atmosphere

used gas: propane  
 flame height: 40mm  
 bottom edge ignition:  
 size EN1101: 200x80mm  
 size EN13772: 560x170mm

#### flowchart EN13773



### EN 1101

Test EN1101 is performed after subjecting the fabric to 1 washing cycle, based on the recommended washing instructions.

flame application time	warp	weft
1s	no ignition	no ignition
2s	no ignition	no ignition
3s	no ignition	no ignition
4s	no ignition	no ignition
5s	no ignition	no ignition
10s	no ignition	no ignition
15s	no ignition	no ignition
20s	no ignition	no ignition

Mean ignition time warp: 0  
 Mean ignition time weft: 0  
 Minimum ignition time: 0

Document number: 201700039  
 Fabric reference: Jest  
 (ecru)  
 Customer: BRU Textiles  
 Satenrozen 2a  
 B-2550 Kontich

Report date: 13/01/2017  
 Date analyses: 12/01/2017 - 13/01/2017  
 Place analyses: Labotex  
 Date of request: 6/01/2017  
 Samples received: 5/01/2017

Testing and conditioning in standard atmosphere, T (20±2)°C and RH (65±4)%

**Specification** **Results** **Remarks** !

### EN13772

warp	face	reverse	reverse	reverse
1st marker thread severed	no	no	no	no
2nd marker thread severed	no	no	no	no
3rd marker thread severed	no	no	no	no
time to severance 3rd marker thread (s)	0	0	0	0
destroyed length (mm)	105	82	112	111
flaming debris	no	no	no	no
weft	face	reverse	face	face
1st marker thread severed	no	no	no	no
2nd marker thread severed	no	no	no	no
3rd marker thread severed	no	no	no	no
time to severance 3rd marker thread (s)	0	0	0	0
destroyed length (mm)	104	140	100	122
flaming debris	no	no	no	no

### EN13772 after washing

warp	face	reverse	reverse	reverse
1st marker thread severed	no	no	no	no
2nd marker thread severed	no	no	no	no
3rd marker thread severed	no	no	no	no
time to severance 3rd marker thread (s)	0	0	0	0
destroyed length (mm)	120	97	100	110
flaming debris	no	no	no	no
weft	face	reverse	face	face
1st marker thread severed	no	no	no	no
2nd marker thread severed	no	no	no	no
3rd marker thread severed	no	no	no	no
time to severance 3rd marker thread (s)	0	0	0	0
destroyed length (mm)	130	87	111	102
flaming debris	no	no	no	no



# Report EN13773

Document number:	201700039	Report date:	13/01/2017
Fabric reference:	Jest (ecru)	Date analyses:	12/01/2017 - 13/01/2017
Customer:	BRU Textiles Satenrozen 2a B-2550 Kontich	Place analyses:	Labotex
		Date of request:	6/01/2017
		Samples received:	5/01/2017

Testing and conditioning in standard atmosphere, T (20+-2)°C and RH (65+-4)%

Specification	Results	Remarks	!
---------------	---------	---------	---

---

### Classification

Class 1	----- X -----
Class 2	-----
Class 3	-----
Class 4 or 5	-----

Labotex certifies that the results mentioned in this report are obtained after testing in accordance with the procedure and equipment specified by the concerned standards, unless noted differently.

Joeri Neys - Laboratory Manager

Labotex has the competence to perform tests in accordance with the requirements of standard NBN EN ISO/IEC 17025. The scope of this accreditation can be obtained on request.

The results in this report only relate to the tested items.

Samples will be returned to the customer with the certificate, if possible. Samples will not be retained, unless specified by the customer. Retained samples will be kept for maximum one year unless a specific retention period is necessary.

This report can not be copied unless in its complete form and with written approval of Labotex (Kontich).

Sampling is performed by the customer. Fabric analysed as received.