

CERTIFICATE OF TESTING

For the Account Of: Bru Textiles
Satenrozen 2a
B2550 Kontich
Belgium
Contact: Brigitte Gyselincx

Client's Identification: FR- One Jest

TEST PERFORMED NY / NJ Port Authority Specifications Governing the Flammability of Drapery and Curtain Materials in Unsprinkled Areas (Appendix A) – 2010
[FAR 25.853(a) Appendix F, as revised February 2, 1995 – 12 second vertical method]

TEST RESULTS

Specimen	Afterflame (s)	Char Length (in)
1	0	3.6
2	0	4.1
3	0	4.5
Average Warp	0	4.1
4	0	4.1
5	0	3.8
6	0	3.9
Average Fill	0	3.9


Tested:
 Initially
 After Laundering
 After Dry Cleaning

NOTES
Test Conditions: 70 ±2°F, 65 ±2% Relative Humidity

- ACCEPTANCE CRITERIA**
- Average Burn Length cannot exceed **8 inches** maximum average.
 - Average Flame Time after removal of the flame source may not exceed **5 seconds**.

CONCLUSION Based on the above Results and Acceptance Criteria, the item tested:
 Complies
 Does Not Comply

CERTIFICATION I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.



 Authorized Signature CR