

Document number: 201703041 Report date: 11/12/2017
 Fabric reference: Batiste FR
 01 snow (0015-1720-17 OJ) Date analyses: 8/12/2017 - 11/12/2017
 Customer: BRU Textiles Place analyses: Labotex
 Satenrozen 2a Date of request: 27/10/2017
 B-2550 Kontich Samples received: 26/10/2017

Testing and conditioning in standard atmosphere, T (20+-2)°C and RH (65+-4)%

Specification	Results	Remarks	!
---------------	---------	---------	---

Burning behaviour of fabrics for curtains drapes

EN 1101


Test EN1101 is performed after subjecting the fabric to 1 washing cycle, based on the recommended washing instructions.

EN13773

conditioning min 24h in standard atmosphere

used gas: propane
 flame height: 40mm
 bottom edge ignition:
 size EN1101: 200x80mm
 size EN13772: 560x170mm

flowchart EN13773



flame application time	warp	weft
1s	no ignition	no ignition
2s	no ignition	no ignition
3s	no ignition	no ignition
4s	no ignition	no ignition
5s	no ignition	no ignition
10s	no ignition	no ignition
15s	no ignition	no ignition
20s	no ignition	no ignition

Mean ignition time warp: 0.0
 Mean ignition time weft: 0.0
 Minimum ignition time: 0.0

Document number: 201703041 Report date: 11/12/2017
 Fabric reference: Batiste FR
 01 snow (0015-1720-17 OJ) Date analyses: 8/12/2017 - 11/12/2017
 Customer: BRU Textiles Place analyses: Labotex
 Satenrozen 2a Date of request: 27/10/2017
 B-2550 Kontich Samples received: 26/10/2017

Testing and conditioning in standard atmosphere, T (20+-2)°C and RH (65+-4)%

Specification	Results	Remarks	!
---------------	---------	---------	---

EN13772 before washing

warp	face	reverse	reverse	reverse
1st marker thread severed	no	no	no	no
2nd marker thread severed	no	no	no	no
3rd marker thread severed	no	no	no	no
time to severance 3rd marker thread (s)	0	0	0	0
destroyed length (mm)	163	189	151	199
flaming debris	no	no	no	no
weft	face	reverse	face	face
1st marker thread severed	no	no	no	no
2nd marker thread severed	no	no	no	no
3rd marker thread severed	no	no	no	no
time to severance 3rd marker thread (s)	0	0	0	0
destroyed length (mm)	177	200	168	127
flaming debris	no	no	no	no

EN13772 after washing

warp	face	reverse	reverse	reverse
1st marker thread severed	no	no	no	no
2nd marker thread severed	no	no	no	no
3rd marker thread severed	no	no	no	no
time to severance 3rd marker thread (s)	0	0	0	0
destroyed length (mm)	154	149	149	129
flaming debris	no	no	no	no
weft	face	reverse	face	face
1st marker thread severed	no	no	no	no
2nd marker thread severed	no	no	no	no
3rd marker thread severed	no	no	no	no
time to severance 3rd marker thread (s)	0	0	0	0
destroyed length (mm)	146	145	161	174
flaming debris	no	no	no	no

Document number:	201703041	Report date:	11/12/2017
Fabric reference:	Batiste FR		
	01 snow (0015-1720-17 OJ)	Date analyses:	8/12/2017 - 11/12/2017
Customer:	BRU Textiles	Place analyses:	Labotex
	Satenrozen 2a	Date of request:	27/10/2017
	B-2550 Kontich	Samples received:	26/10/2017

Testing and conditioning in standard atmosphere, T (20+-2)°C and RH (65+-4)%

Specification	Results	Remarks	!
---------------	---------	---------	---

Classification



Class 1	----- X -----
Class 2	-----
Class 3	-----
Class 4 or 5	-----



Labotex certifies that the results mentioned in this report are obtained after testing in accordance with the procedure and equipment specified by the concerned standards, unless noted differently.



Joeri Neys - Laboratory Manager

Labotex has the competence to perform tests in accordance with the requirements of standard NBN EN ISO/IEC 17025. The scope of this accreditation can be obtained on request.

The results in this report only relate to the tested items.

Samples will be returned to the customer with the certificate, if possible. Samples will not be retained, unless specified by the customer. Retained samples will be kept for maximum one year unless a specific retention period is necessary.

This report can not be copied unless in its complete form and with written approval of Labotex (Kontich).

Sampling is performed by the customer. Fabric analysed as received.

The uncertainty and the description of the methods are available at the lab on request.