



Textile Testing

553 76th Street · Byron Center, MI 49315 Phone: 616.559.6123 Fax: 616.559.6119



TESTING CERT. #3193.01

Report Number: 51054

Date: 3-8-2012

For the Account Of: Bru Textiles
Satenrozen 2a
B-2550 Kontich
Belgium
Contact: Tineke Verbruggen

Client's Identification: Gossy

Test Performed Boston Fire Test BFD IX- 1 May 2003

TEST DATA

<u>Specimen #</u>	<u>AFTERFLAME</u> (seconds)	<u>CHAR LENGTH</u> (flame propagation)	<u>PROPAGATION</u> <u>AFTERGLOW</u> (seconds)	<u>NON PROPAGATING</u> <u>AFTERGLOW</u> (seconds)
1	0	5.0	0	0
2	0	5.0	0	0
3	0	5.3	0	0
4	0	5.0	0	0
5	0	5.0	0	0
6	0	5.0	0	0

NOTES

Test Conditions: 70 ±2°F, 65 ±2% Relative Humidity

Sampling Method: As Received


ACCEPTANCE CRITERIA

After Flame 2.0 seconds maximum
 Flame Propagation Distance 6.0 inches maximum from bottom edge of specimen
 Propagation Afterglow 40.0 seconds maximum
 Non Propagating Afterglow 80.0 seconds maximum (in charred area)

CONCLUSION Based on the above Results and Acceptance Criteria, the item tested:

- Complies
- Does Not Comply

CERTIFICATION: I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.



Authorized Signature