

財團法人防焰安全中心基金會
 FOUNDATION OF FIRE RETARDANT SAFETY CENTER

試驗報告書
 TEST REPORT

COPY

Date : 2013/10/21

Report No. : N1021137


Client : ANDARI CO., LTD.

Address : NO. 440, SEC. 4, REN AI RD., XIN YI DIST., TAIPEI CITY 11073, TAIWAN (R.O.C.)

Description of Sample			
Kinds of Products	CURTAIN	Brand Name	FR-7030 GOSSY
Material and Blending Ratio	POLYESTER 100%	Construction of Fabric	WEAVING
Kinds of Laundering as Pretreatment	ORIGINAL · WASHING	Weight of Unit Area	116 g/m ²
Count of Threads	15's/1 × 15's/1	Density	13/in × 13/in
Note	Test Method : CNS 10285 L3196		
Result			
Determination	PASSED		
Test Date	2013/10/17	Test Number	NB-02-6665

President of FFRSC : HUNG CHUN-AN

Foundation of Fire Retardant Safety Center
 1F., NO. 42, Lane 76, Sed. 3, Jhongyang Rd.,
 Tucheng City, Taipei, Count 236, TAIWAN R.O.C.
 Tel : (02)22689119 Fax : (02)22689257





【A】 Flammability Test Results of Original

(1) 45° Micro Burner Test - A1

(2) 45° Coil Test

Numerical Criteria	Run No.	Afterflame Time (sec)	Afterglow Time (sec)	Charred Area (cm ²)
		X ≤ 3	X ≤ 5	X ≤ 30
60 sec Flame Contact	No. 1	0	0	6
	No. 2	0	0	6
	No. 3	0	0	7
3 sec Flame Contact after Flame Burning	No. 1	0	0	7
	No. 2	0	0	6

Run No.	Numbers of Flame Contact
	X ≥ 3
No. 1	3
No. 2	4
No. 3	3
No. 4	3
No. 5	3

心

【B】 Flammability Test Results after Washing

(1) 45° Micro Burner Test - A1

(2) 45° Coil Test

Numerical Criteria	Run No.	Afterflame Time (sec)	Afterglow Time (sec)	Charred Area (cm ²)
		X ≤ 3	X ≤ 5	X ≤ 30
60 sec Flame Contact	No. 1	0	0	6
	No. 2	0	0	6
	No. 3	0	0	6
3 sec Flame Contact after Flame Burning	No. 1	0	0	5
	No. 2	0	0	5

Run No.	Numbers of Flame Contact
	X ≥ 3
No. 1	3
No. 2	3
No. 3	3
No. 4	3
No. 5	4