

ANALYSIS REPORT
SCC Accreditation No.: 40‡

Mr Tineke Verbruggen
Bru Textiles nv

Date: April 24, 2014
Report: 3489-004-73206A

IDENTIFICATION: 5. FR One: Venere
Received: March 26, 2014

STANDARD:

TEST: Flame Tests of Flame-Resistant Fabrics and Films - Small-Flame Test - As received
CAN/ULC-S109-03

TEST CONDITIONS: Gas used : methane; Gas pressure used: $2\frac{1}{2} \pm \frac{1}{4}$ psi;
Specimens tested as received only.
Conditioning of the specimens: 105°C, 30 min
Cooling time: dessiccator
Date tested: April 15, 2014

RESULTS:

Individual Data

Afterflame (s) - Residues - Length: 0 0 0 0 0

Afterflame (s) - Residues - Width: 0 0 0 0 0


Damaged length (mm) - Length: 157 162 155 160 159

Damaged length (mm) - Width: 130 148 162 154 147


Damaged length (mm) - Average: 153.4

REQUIREMENTS: Portions or residues of the material which break or drip from the test specimens shall not continue to flame for more than 2 seconds on the floor of the test cabinet.
Maximum Average Damaged Length for 10 specimens : 165 mm;
Maximum Damaged Length for any specimen : 190 mm.

Prepared by:


Geneviève Auger, Tech.
Technician

Approved by:


Valério Izquierdo, B. Eng. Textile
Laboratory Director

Date: April 24, 2014

****For any information concerning this report, please contact Valério Izquierdo.****

The reports are identified by an alphanumeric code, the last character refers to the number of revision(s), this is emitted in ascending order. The samples in relation to this test are retained for a period of 30 days following the expedition day of the written report, unless other instructions are received. The fees for all services after the tests are 125.00 \$ per hour and for appraisal in Court, 195.00\$ per hour. The above reported results refer exclusively to the samples submitted for evaluation. This analysis report cannot be partly used or reproduced, unless in whole, without CTT Group prior written consent. ‡ CTT Group is accredited by the SCC for specific tests as listed on www.scc.ca. For customer's complete address, please refer to the front page.

ANALYSIS REPORT
SCC Accreditation No.: 40‡

Mr Tineke Verbruggen
Bru Textiles nv

Date: April 24, 2014
Report: 3489-004-73206A

IDENTIFICATION: 5. FR One: Venere
Received: March 26, 2014

STANDARD:

TEST: Flame Tests of Flame-Resistant Fabrics and Films - Large-Flame Test - As received
CAN/ULC-S109-03

TEST CONDITIONS: Specimens placed in a drying oven at $105 \pm 2^{\circ}\text{C}$ for 30 minutes, then allowed to cool in a desiccator;
Gas used : methane; Gas pressure used: $2\frac{1}{2} \pm \frac{1}{4}$ psi;
Specimens tested, in folds, as received only.
Date tested: April 16, 2014

RESULTS: Individual Data

Afterflame Dripping (s) - Length: 0 0


Afterflame Dripping (s) - Width: 0 0

Damaged length (mm) - Length: 84 110


Damaged length (mm) - Width: 104 93

REQUIREMENTS: Portions or residues of the material which break or drip from the test specimens shall not continue to flame for more than 2 seconds on the floor of the test cabinet.
Damaged Length : shall not exceed 635 mm.

Prepared by:


Geneviève Auger, Tech.
Technician

Approved by:


Valério Izquierdo, B. Eng. Textile
Laboratory Director

Date: April 24, 2014

****For any information concerning this report, please contact Valério Izquierdo.****

The reports are identified by an alphanumeric code, the last character refers to the number of revision(s), this is emitted in ascending order. The samples in relation to this test are retained for a period of 30 days following the expedition day of the written report, unless other instructions are received. The fees for all services after the tests are 125.00 \$ per hour and for appraisal in Court, 195.00\$ per hour. The above reported results refer exclusively to the samples submitted for evaluation. This analysis report cannot be partly used or reproduced, unless in whole, without CTT Group prior written consent. ‡ CTT Group is accredited by the SCC for specific tests as listed on www.scc.ca. For customer's complete address, please refer to the front page.