



**Textile Testing**

553 76<sup>th</sup> Street · Byron Center, MI 49315 Phone: 616.559.6123 Fax: 616.559.6119



TESTING CERT. #3193.01

Report Number: 61684

Date: 11-13-2013

For the Account Of: Bru Textiles  
Satenrozen 2A  
2550 Kontich  
Belgium  
Contact: Tineke Verbruggen

Client's Identification: FR One Venere

**Test Performed Boston Fire Test BFD IX- 1 May 2003**

**TEST RESULTS**

<u>Specimen #</u>	<u>AFTERFLAME</u> (seconds)	<u>CHAR LENGTH</u> (flame propagation)	<u>PROPAGATION</u> <u>AFTERGLOW</u> (seconds)	<u>NON PROPAGATING</u> <u>AFTERGLOW</u> (seconds)
1	0	3.1	0	0
2	0	3.1	0	0
3	0	2.8	0	0
4	0	2.5	0	0
5	0	2.0	0	0
6	0	2.9	0	0

**NOTES**

**Test Conditions:** 70 ±2°F, 65 ±2% Relative Humidity

**Sampling Method:** As Received

**ACCEPTANCE CRITERIA**

After Flame 2.0 seconds maximum  
 Flame Propagation Distance 6.0 inches maximum from bottom edge of specimen  
 Propagation Afterglow 40.0 seconds maximum  
 Non Propagating Afterglow 80.0 seconds maximum (in charred area)

**CONCLUSION** Based on the above Results and Acceptance Criteria, the item tested:

- Complies
- Does Not Comply

CERTIFICATION: I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

Authorized Signature-MB